

21. (Amended) A process for forming a pattern of fluorescent substance into the cell of a fluorescent substance display substrate, wherein a resin composition (A) layer, consisting essentially of an acrylic polymer (a) having a weight average molecular weight of 10000 to 300000 and an acid number of 80 to 250 mgKOH/g, a fluorescent substance (b), a compound containing at least one ethylenically unsaturated group (c) having a viscosity of 5-15000 mPa.sec at 20°C, and a polymerization inhibitor (d), and a photosensitive resin composition (B) layer are formed inside the cell, and then they are exposed, developed and baked, wherein the photosensitive resin composition (B) layer is formed in the cell after the resin composition (A) layer is formed.

F-1
cancel
22. (Amended) A process for forming a pattern of fluorescent substance into the cell of a fluorescent substance display substrate comprising providing inside the cell two separate layers which are (i) a resin composition (A) layer and (ii) a photosensitive resin composition (B) layer, wherein the resin composition (A) layer, consisting essentially of an acrylic polymer (a) having a weight average molecular weight of 10000 to 300000 and an acid number of 80 to 250 mgKOH/g, a fluorescent substance (b), a compound containing at least one ethylenically unsaturated group (c) having a viscosity of 5-15000 mPa.sec at 20°C, and a polymerization inhibitor (d), and the photosensitive resin composition (B) layer are formed inside the cell, and then they are exposed, developed and baked, wherein the photosensitive resin composition (B) layer is formed in the cell after the resin composition (A) layer is formed.
